



### Fluoroelastomer (FKM)

FKM fluoroelastomer offers excellent resistance to strong acids, oils, gasoline, chlorate solvents and aliphatic and aromatic hydrocarbons. Not recommended for use with amines, esters, ketones and steam.

SERVICE LIMITS							
Grade	Thickness (Inches)	Width (Inches)	Durometer Hardness Shore A±5	Tensile	Elongation	Temp	Specifications
A	1/16 thru 1/4	36 & 48	75	1650	165	-18°C to 204°C (400°F)	ASTM D-2000 2HK707B38E078Z

"Commercial Grade" FKM also available

Properties and application parameters shown throughout this datasheet are typical. Your specific application should not be undertaken without independent study and evaluation for suitability. For specific application recommendations consult TEADIT. Failure to select proper sealing products could result in property damage and/or serious personal injury. Specifications are subject to change without notice. This edition supersedes all previous issues.